

2003B133B

Response to OA of 1/11/08

RECEIVED
CENTRAL FAX CENTER
JUN 09 2008

IN THE CLAIMS:

1. (Currently amended) A copolymer comprising an isoolefin and a multiolefin, the copolymer being substantially free of long chain branching; wherein the copolymer has a $g'_{vis,avg}$ greater than or equal to 0.978 as determined by triple detection SEC.
2. (previously presented) The copolymer of claim 1, wherein the multiolefin is a conjugated diene.
3. (currently amended) The copolymer of claim 1, wherein the multiolefin content is from 0.5 wt%.
4. – 6. (cancelled)
7. (currently amended) A copolymer comprising isobutylene and isoprene, the copolymer being substantially free of long chain branching; wherein the copolymer has a $g'_{vis,avg}$ greater than or equal to 0.978 as determined by triple detection SEC.
8. (currently amended) The copolymer of claim 7, wherein the isoprene content is from 0.5 wt%.
9. – 11. (cancelled)
12. (currently amended) A copolymer produced by the process comprising contacting an isoolefin, a multiolefin, one or more Lewis acid(s), one or more initiator(s), and a diluent comprising one or more hydrofluorocarbon(s) (HFC's); wherein the copolymer is substantially free of long chain branching and wherein the copolymer has a $g'_{vis,avg}$ greater than or equal to 0.978 as determined by triple detection SEC.
13. (previously presented) The copolymer of claim 12, wherein the multiolefin is a conjugated diene.

2003B133B

Response to OA of 1/11/08

14. (currently amended) The copolymer of claim 12, wherein the multiolefin content is from 0.5 wt%.
15. - 17. (cancelled)
18. (previously presented) The copolymer of claim 12, wherein one or more hydrofluorocarbon(s) is represented by the formula: $C_xH_yF_z$ wherein x is an integer from 1 to 40 and y and z are integers of one or more.
19. (previously presented) The copolymer of claim 18, wherein x is from 1 to 10.
20. - 21. (cancelled)
22. (previously presented) The copolymer of claim 12, wherein the one or more hydrofluorocarbon(s) is independently selected from the group consisting of fluoromethane; difluoromethane; trifluoromethane; fluoroethane; 1,1-difluoroethane; 1,2-difluoroethane; 1,1,1-trifluoroethane; 1,1,2-trifluoroethane; 1,1,1,2-tetrafluoroethane; 1,1,2,2-tetrafluoroethane; 1,1,1,2,2-pentafluoroethane; 1-fluoropropane; 2-fluoropropane; 1,1-difluoropropane; 1,2-difluoropropane; 1,3-difluoropropane; 2,2-difluoropropane; 1,1,1-trifluoropropane; 1,1,2-trifluoropropane; 1,1,3-trifluoropropane; 1,2,2-trifluoropropane; 1,2,3-trifluoropropane; 1,1,1,2-tetrafluoropropane; 1,1,1,3-tetrafluoropropane; 1,1,2,2-tetrafluoropropane; 1,1,2,3-tetrafluoropropane; 1,1,3,3-tetrafluoropropane; 1,2,2,3-tetrafluoropropane; 1,1,1,2,2-pentafluoropropane; 1,1,1,2,3-pentafluoropropane; 1,1,1,3,3-pentafluoropropane; 1,1,2,2,3-pentafluoropropane; 1,1,2,3,3-pentafluoropropane; 1,1,1,2,2,3-hexafluoropropane; 1,1,1,2,3,3-hexafluoropropane; 1,1,1,3,3,3-hexafluoropropane; 1,1,1,2,2,3,3-heptafluoropropane; 1,1,1,2,3,3,3-heptafluoropropane; 1-fluorobutane; 2-fluorobutane; 1,1-difluorobutane; 1,2-difluorobutane; 1,3-difluorobutane; 1,4-difluorobutane; 2,2-difluorobutane; 2,3-difluorobutane; 1,1,1-trifluorobutane; 1,1,2-trifluorobutane; 1,1,3-trifluorobutane; 1,1,4-trifluorobutane; 1,2,2-trifluorobutane; 1,2,3-trifluorobutane; 1,3,3-trifluorobutane; 2,2,3-trifluorobutane; 1,1,1,2-tetrafluorobutane; 1,1,1,3-tetrafluorobutane; 1,1,1,4-tetrafluorobutane; 1,1,2,2-tetrafluorobutane; 1,1,2,3-tetrafluorobutane; 1,1,2,4-tetrafluorobutane; 1,1,3,3-

Page 3 of 15

H:\BPC\LA\W\Prosecution\2003\2003B133B\US-2004 April 11 Response to OA.doc

2003B133B

Response to OA of 1/11/08

tetrafluorobutane; 1,1,3,4-tetrafluorobutane; 1,1,4,4-tetrafluorobutane; 1,2,2,3-tetrafluorobutane; 1,2,2,4-tetrafluorobutane; 1,2,3,3-tetrafluorobutane; 1,2,3,4-tetrafluorobutane; 2,2,3,3-tetrafluorobutane; 1,1,1,2,2-pentafluorobutane; 1,1,1,2,3-pentafluorobutane; 1,1,1,2,4-pentafluorobutane; 1,1,1,3,3-pentafluorobutane; 1,1,1,3,4-pentafluorobutane; 1,1,1,4,4-pentafluorobutane; 1,1,2,2,3-pentafluorobutane; 1,1,2,2,4-pentafluorobutane; 1,1,2,3,3-pentafluorobutane; 1,1,2,3,4-pentafluorobutane; 1,1,2,4,4-pentafluorobutane; 1,1,3,3,4-pentafluorobutane; 1,2,2,3,3-pentafluorobutane; 1,2,2,3,4-pentafluorobutane; 1,1,1,2,2,3-hexafluorobutane; 1,1,1,2,2,4-hexafluorobutane; 1,1,1,2,3,3-hexafluorobutane; 1,1,1,2,3,4-hexafluorobutane; 1,1,1,2,4,4-hexafluorobutane; 1,1,1,3,3,4-hexafluorobutane; 1,1,1,3,4,4-hexafluorobutane; 1,1,1,4,4,4-hexafluorobutane; 1,1,2,2,3,3-hexafluorobutane; 1,1,2,2,3,4-hexafluorobutane; 1,1,2,2,4,4-hexafluorobutane; 1,1,2,3,3,4-hexafluorobutane; 1,1,2,3,4,4-hexafluorobutane; 1,2,2,3,3,4-hexafluorobutane; 1,1,1,2,2,3,3-heptafluorobutane; 1,1,1,2,2,4,4-heptafluorobutane; 1,1,1,2,2,3,4-heptafluorobutane; 1,1,1,2,3,3,4-heptafluorobutane; 1,1,1,2,3,4,4-heptafluorobutane; 1,1,1,2,4,4,4-heptafluorobutane; 1,1,1,3,3,4,4-heptafluorobutane; 1,1,1,2,2,3,3,4-octafluorobutane; 1,1,1,2,2,3,4,4-octafluorobutane; 1,1,1,2,3,3,4,4-octafluorobutane; 1,1,1,2,2,4,4,4-octafluorobutane; 1,1,1,2,3,4,4,4-octafluorobutane; 1,1,1,2,2,3,3,4,4-nonafluorobutane; 1,1,1,2,2,3,4,4,4-nonafluorobutane; 1-fluoro-2-methylpropane; 1,1-difluoro-2-methylpropane; 1,3-difluoro-2-methylpropane; 1,1,1-trifluoro-2-methylpropane; 1,1,3-trifluoro-2-methylpropane; 1,3-difluoro-2-(fluoromethyl)propane; 1,1,1,3-tetrafluoro-2-methylpropane; 1,1,3,3-tetrafluoro-2-methylpropane; 1,1,3-trifluoro-2-(fluoromethyl)propane; 1,1,1,3,3-pentafluoro-2-methylpropane; 1,1,3,3-tetrafluoro-2-(fluoromethyl)propane; 1,1,1,3-tetrafluoro-2-(fluoromethyl)propane; fluorocyclobutane; 1,1-difluorocyclobutane; 1,2-difluorocyclobutane; 1,3-difluorocyclobutane; 1,1,2-trifluorocyclobutane; 1,1,3-trifluorocyclobutane; 1,2,3-trifluorocyclobutane; 1,1,2,2-tetrafluorocyclobutane; 1,1,3,3-tetrafluorocyclobutane; 1,1,2,2,3-pentafluorocyclobutane; 1,1,2,3,3-pentafluorocyclobutane; 1,1,2,2,3,3-hexafluorocyclobutane; 1,1,2,2,3,4-hexafluorocyclobutane; 1,1,2,3,3,4-hexafluorocyclobutane; 1,1,2,2,3,3,4-heptafluorocyclobutane; vinyl fluoride; 1,1-difluoroethene; 1,2-difluoroethene; 1,1,2-trifluoroethene; 1-fluoropropene; 1,1-difluoropropene; 1,2-difluoropropene; 1,3-difluoropropene; 2,3-difluoropropene; 3,3-difluoropropene; 1,1,2-trifluoropropene;

Page 4 of 15

I:\DPC\AW\Preservation\DMCC\Preservation\2003\2003B133\BUS\2003B133B-US-2008 April 11 Response to OA.doc

2003B133B

Response to OA of 1/11/08

1,1,3-trifluoropropene; 1,2,3-trifluoropropene; 1,3,3-trifluoropropene; 2,3,3-trifluoropropene; 3,3,3-trifluoropropene; 1-fluoro-1-butene; 2-fluoro-1-butene; 3-fluoro-1-butene; 4-fluoro-1-butene; 1,1-difluoro-1-butene; 1,2-difluoro-1-butene; 1,3-difluoropropene; 1,4-difluoro-1-butene; 2,3-difluoro-1-butene; 2,4-difluoro-1-butene; 3,3-difluoro-1-butene; 3,4-difluoro-1-butene; 4,4-difluoro-1-butene; 1,1,2-trifluoro-1-butene; 1,1,3-trifluoro-1-butene; 1,1,4-trifluoro-1-butene; 1,2,3-trifluoro-1-butene; 1,2,4-trifluoro-1-butene; 1,3,3-trifluoro-1-butene; 1,3,4-trifluoro-1-butene; 1,4,4-trifluoro-1-butene; 2,3,3-trifluoro-1-butene; 2,3,4-trifluoro-1-butene; 2,4,4-trifluoro-1-butene; 3,3,4-trifluoro-1-butene; 3,4,4-trifluoro-1-butene; 4,4,4-trifluoro-1-butene; 1,1,2,3-tetrafluoro-1-butene; 1,1,2,4-tetrafluoro-1-butene; 1,1,3,3-tetrafluoro-1-butene; 1,1,3,4-tetrafluoro-1-butene; 1,1,4,4-tetrafluoro-1-butene; 1,2,3,3-tetrafluoro-1-butene; 1,2,3,4-tetrafluoro-1-butene; 1,2,4,4-tetrafluoro-1-butene; 1,3,3,4-tetrafluoro-1-butene; 1,3,4,4-tetrafluoro-1-butene; 1,4,4,4-tetrafluoro-1-butene; 2,3,3,4-tetrafluoro-1-butene; 2,3,4,4-tetrafluoro-1-butene; 2,4,4,4-tetrafluoro-1-butene; 3,3,4,4-tetrafluoro-1-butene; 3,4,4,4-tetrafluoro-1-butene; 1,1,2,3,3-pentafluoro-1-butene; 1,1,2,3,4-pentafluoro-1-butene; 1,1,2,4,4-pentafluoro-1-butene; 1,1,3,3,4-pentafluoro-1-butene; 1,1,3,4,4-pentafluoro-1-butene; 1,1,4,4,4-pentafluoro-1-butene; 1,2,3,3,4-pentafluoro-1-butene; 1,2,3,4,4-pentafluoro-1-butene; 1,2,4,4,4-pentafluoro-1-butene; 2,3,3,4,4-pentafluoro-1-butene; 2,3,4,4,4-pentafluoro-1-butene; 3,3,4,4,4-pentafluoro-1-butene; 1,1,2,3,3,4-hexafluoro-1-butene; 1,1,2,3,4,4-hexafluoro-1-butene; 1,1,2,4,4,4-hexafluoro-1-butene; 1,2,3,3,4,4-hexafluoro-1-butene; 1,2,3,4,4,4-hexafluoro-1-butene; 2,3,3,4,4,4-hexafluoro-1-butene; 1,1,2,3,3,4,4-heptafluoro-1-butene; 1,1,2,3,4,4,4-heptafluoro-1-butene; 1,1,3,3,4,4,4-heptafluoro-1-butene; 1,2,3,3,4,4,4-heptafluoro-1-butene; 1-fluoro-2-butene; 2-fluoro-2-butene; 1,1-difluoro-2-butene; 1,2-difluoro-2-butene; 1,3-difluoro-2-butene; 1,4-difluoro-2-butene; 2,3-difluoro-2-butene; 1,1,1-trifluoro-2-butene; 1,1,2-trifluoro-2-butene; 1,1,3-trifluoro-2-butene; 1,1,4-trifluoro-2-butene; 1,2,3-trifluoro-2-butene; 1,2,4-trifluoro-2-butene; 1,1,1,2-tetrafluoro-2-butene; 1,1,1,3-tetrafluoro-2-butene; 1,1,1,4-tetrafluoro-2-butene; 1,1,2,3-tetrafluoro-2-butene; 1,1,2,4-tetrafluoro-2-butene; 1,2,3,4-tetrafluoro-2-butene; 1,1,1,2,3-pentafluoro-2-butene; 1,1,1,2,4-pentafluoro-2-butene; 1,1,1,3,4-pentafluoro-2-butene; 1,1,1,4,4-pentafluoro-2-butene; 1,1,2,3,4-pentafluoro-2-butene; 1,1,2,4,4-pentafluoro-2-butene; 1,1,1,2,3,4-hexafluoro-2-butene; 1,1,1,2,4,4-hexafluoro-2-butene; 1,1,1,3,4,4-hexafluoro-2-

Page 5 of 15

I:\P\14\W\14000000\14000000\MCC\Production\2003\200311\11\14\US\2003B133B-US-2008 April 11 Response to OA.doc

2003B133B

Response to OA of 1/11/08

butene; 1,1,1,4,4,4-hexafluoro-2-butene; 1,1,2,3,4,4-hexafluoro-2-butene; 1,1,1,2,3,4,4,4-heptafluoro-2-butene; 1,1,1,2,4,4,4-heptafluoro-2-butene; and mixtures thereof.

23. (cancelled)
24. (previously presented) The copolymer of claim 12, wherein the diluent comprises from 15 to 100 volume % HFC based upon the total volume of the diluent.
25. – 26. (cancelled)
27. (previously presented) The copolymer of claim 12, wherein the diluent further comprises a hydrocarbon, a non-reactive olefin, and/or an inert gas.
28. (currently amended) The copolymer of claim 12, wherein the diluent further comprises a halogenated hydrocarbon other than an HFC.
29. (cancelled)
30. (previously presented) The copolymer of claim 12, wherein the one or more Lewis acid(s) is represented by a formula selected from the group consisting of
- a) MX_4
wherein M is a Group 4, 5, or 14 metal; and
each X is a halogen;
 - b) MR_nX_{4-n}
wherein M is Group 4, 5, or 14 metal;
each R is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;
n is an integer from 0 to 4; and
each X is a halogen;
 - c) $M(RO)_nR'_mX_{4-(m+n)}$
wherein M is Group 4, 5, or 14 metal;

2003B133B

Response to OA of 1/11/08

each RO is a monovalent C₁ to C₃₀ hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;
 each R' is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;
 n is an integer from 0 to 4;
 m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and
 each X is a halogen; and
 d) $M(RC=OO)_n R'_m X_{4-(n+m)}$
 wherein M is Group 4, 5, or 14 metal;
 each RC=OO is a monovalent C₂ to C₃₀ hydrocarbacyl radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylalkylacyloxy, alkylarylacyloxy radicals;
 each R' is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;
 n is an integer from 0 to 4;
 m is an integer from 0 to 4, wherein the sum of n and m is not more than 4; and
 each X is a halogen.

31. - 33 (cancelled)

34. (currently amended) The copolymer of claim 12, wherein the one or more Lewis acid(s) is represented by a formula selected from the group consisting of:

a) MOX_3

wherein M is a Group 5 metal; and

each X is a halogen;

b) MX_3 ;

wherein M is a Group 13 metal; and

each X is a halogen;

c) $MR_n X_{3-n}$

wherein M is a Group 13 metal;

each R is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 1 to 3; and

Page 7 of 15

\\RPCLAW\prosecutor\USDOC Prosecution\2003\2003\11\23\B\US\2003B\33R-US-2008 April 11 Response to OA.doc

2003B133B

Response to OA of 1/11/08

each X is a halogen;

$$d) M(RO)_n R'_m X_{3-(m+n)}$$

wherein M is a Group 13 metal;

each RO is a monovalent C₁ to C₃₀ hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

each R¹ is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 3;

m is an integer from 0 to 3, wherein the sum of n and m is from 1 to 3; and

each X is a halogen; and

$$e) M(RC=OO)_n R'_m X_{3-(m+n)};$$

wherein M is a Group 13 metal;

each RC=OO is a monovalent hydrocarbacyl radical independently selected from the group independently selected from the C₂ to C₃₀ group consisting of an alkacyloxy, arylacyloxy, arylalkylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 3:

m is a integer from 0 to 3, wherein the sum of n and m is from 1 to 3: and

each X is a halogen.

35. - 38. (cancelled)

39. (currently amended) The copolymer of claim 12, wherein the one or more Lewis acid(s) is represented by a formula selected from the group consisting of:

a) MX_v

wherein M is a Group 15 metal;

each X is a halogen; and

y is 3, 4 or 5;

b) $MR_{\pi} X_{y-\alpha}$;

wherein M is a Group 15 metal;

each R is a monovalent C₁ to C₁₂ hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

2003B133B

Response to OA of 1/11/08

n is an integer from 0 to 4;

y is 3, 4 or 5, wherein n is less than y ; and

each X is a halogen;

c) $M(RO)_n R'_m X_{y-(m+n)}$;

wherein M is a Group 15 metal,

each RO is a monovalent C_1 to C_{30} hydrocarboxy radical independently selected from the group consisting of an alkoxy, aryloxy, arylalkoxy, alkylaryloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y ; and

each X is a halogen; and

d) $M(RC=OO)_n R'_m X_{y-(m+n)}$;

wherein M is a Group 15 metal;

each $RC=OO$ is a monovalent C_2 to C_{30} hydrocarbacyloxy radical independently selected from the group consisting of an alkacyloxy, arylacyloxy, arylalkylacyloxy, alkylarylacyloxy radicals;

each R' is a monovalent C_1 to C_{12} hydrocarbon radical independently selected from the group consisting of an alkyl, aryl, arylalkyl, alkylaryl and cycloalkyl radicals;

n is an integer from 0 to 4;

m is an integer from 0 to 4;

y is 3, 4 or 5, wherein the sum of n and m is less than y ; and

each X is a halogen.

40. – 45. (cancelled)

46. (previously presented) The copolymer of claim 12, wherein the one or more initiator(s) comprise a hydrogen halide, a carboxylic acid, a carboxylic acid halide, a sulfonic acid, an alcohol, a phenol, a polymeric halide, a tertiary alkyl halide, a tertiary aralkyl halide, a tertiary alkyl ester, a tertiary aralkyl ester, a tertiary alkyl ether, a tertiary aralkyl ether, an alkyl halide, an aryl halide, an alkylaryl halide or an arylalkylacid halide.

Page 9 of 15

\\BPCLAW\Prosecution\EMOC Prosecution\2003\2003B133B\US\2003B133B-US-2008 April 11 Response to OA.doc

2003B133B

Response to OA of 1/11/08

47. - 49. (cancelled)
50. (previously presented) The copolymer of claim 12, wherein the one or more initiator(s) further comprise a weakly-coordinating anion.
51. (previously presented) The copolymer of claim 12, wherein the one or more initiator(s) comprise greater than 30 ppm water (based upon weight).
52. (previously presented) The copolymer of claim 12, wherein the contacting further comprises contacting one or more monomer(s) independently selected from the group consisting of olefins, alpha-olefins, disubstituted olefins, isoolefins, conjugated dienes, non-conjugated dienes, styrenics, substituted styrenics, and vinyl ethers.
53. (cancelled)
54. (previously presented) The copolymer of claim 7, wherein the copolymer is halogenated to form a halogenated copolymer.
55. - 57. (cancelled)
58. (currently amended) The copolymer of claim 7, wherein the copolymer has a Mw of greater than 10,000.
59. - 61. (cancelled)
62. (currently amended) The copolymer of claim 7, wherein the copolymer has a MWD from about 2 to about 5.
63. - 69. (cancelled)
70. (Withdrawn) A blend comprising the copolymer of claim 7 and a secondary rubber independently from the group consisting of at least one of natural rubber,

Page 10 of 15

I:\DPC\LA\W\Prosecution\VMCC Prosecution\2003\2003B133B\US20031123B-US-2008 April 11 Response to OA.doc

2003B133B

Response to OA of 1/11/08

polyisoprene rubber, poly(styrene-co-butadiene) rubber (SBR), polybutadiene rubber (BR), poly(isoprene-co-butadiene) rubber (IBR), styrene-isoprene-butadiene rubber (SIBR), ethylene-propylene rubber (EPR), ethylene-propylene-diene rubber (EPDM), polysulfide, isobutylene/cyclopentadiene copolymer rubber, isobutylene/methyl cyclopentadiene copolymer rubber, nitrile rubber, propylene oxide polymers, star-branched butyl rubber and halogenated star-branched butyl rubber, brominated butyl rubber, chlorinated butyl rubber, star-branched polyisobutylene rubber, star-branched brominated butyl (polyisobutylene/isoprene copolymer) rubber; poly(isobutylene-co-*p*-methylstyrene) and halogenated poly(isobutylene-co-*p*-methylstyrene), halogenated poly(isobutylene-co-isoprene-co-*p*-methylstyrene), poly(isobutylene-co-isoprene-co-styrene), halogenated poly(isobutylene-co-isoprene-co-styrene), poly(isobutylene-co-isoprene-co- α -methylstyrene) halogenated poly(isobutylene-co-isoprene-co- α -methylstyrene), and mixtures thereof.

- 71 (new) The copolymer of claim 7, wherein the copolymer has a $g'_{vis.avg.}$ from greater than or equal to 0.980 as determined by triple detection SEC.